

BUILT BY
YOUTM
backed by **ARDEX**



ARDEX AMERICAS | Engineered Concrete Repair Systems

	Structural Repair	Single Component	Polymer Modified	Corrosion Inhibitor	Micro silica	Horizontal	Vertical	Overhead	Form & Pour	Pumpable	Trowel-Grade	Walk on or seal	Minimum Thickness neat	Maximum Thickness w/aggregate
ARDEX B 40™	•	•	•	•	•	•			•	•		6 hours	1/2" to 4" neat (12 mm to 10.cm)	9" (23 cm) with aggregate
ARDEX B 24™	•	•	•	•		•					•	Walk: 4-6 hours Seal: 3-7 days	1/4" to 2" neat (6 mm to 5 cm)	8" (20 cm) with aggregate
ARDEX CP™		•	•			•	•				•	Walk: 2 hours Seal: 4 days	1/4" to 1/2" neat (6 to 12 mm)	1" (2.5 cm) with aggregate
ARDEX CD™		•	•			•	•				•	2 hours	1/16" (1.5 mm)	1/8 to 1/2" (3 to 12 mm) in small defined areas
ARDEX CD FINE™		•	•			•	•				•	2 hours	1/32" (0.75 mm)	1/8 to 1/2" (3 to 12 mm) in small defined areas
ARDEX K 301™		•	•			•				•		3 hours	1/4" (6 mm) neat	3/4 to 2" neat (18 mm to 5 cm) with aggregate
ARDEX CG Concrete Guard™		•				•	•				•	24 hours	N/A	N/A
ARDEX ARDIFIX™						•						45 minutes	N/A	No Limits
ARDEX OVP™		•	•				•	•			•	2-3 hours	Featheredge	Any in well-defined areas
ARDEX TWP™		•	•				•				•	15-60 minutes	Featheredge	Any in well-defined areas
ARDEX B 20™	•	•	•	•			•	•			•	3-7 days	1/4" (6 mm)	2" (5 cm) 8" (20 cm) in 2" lifts
ARDEX EP 2000™						•						Walk: 6 Install: 16	N/A	N/A
ARDEX P 71™		•				•						wet	N/A	N/A

The chart information represents basic product recommendations. Always refer to the ARDEX Technical Data Sheets or website prior to installation for specific product installation guidelines. ARDEX Technical Department can be reached at 888-512-7339

AF - 173 01/26
www.ardexamericas.com