ARDEX K 15®

Premium Self-Leveling Underlayment

Choose the Benchmark - ARDEX K 15® is the original and the most specified self-leveler in North America.

Install over: interior concrete, terrazzo, ceramic and quarry tile, epoxy coating systems, wood, metal and non-water soluble adhesive residue on concrete; can be installed over concrete treated with certain curing compounds

Key Features

- Formulated with a special blend of polymers
- Can be installed over wood or metal to a thickness of 1/2" (12.7 mm)
- Pourable with the ROVER® Rolling Barrel Cart;
 Pumpable with the AMP® Automatic Mixing Pumps
- Interior use
- Use on, above or below grade
- Mixes with water

Installation

- General priming recommendations:
 - Concrete: ARDEX P 51[™] Primer
 - Most non-porous substrates, epoxy coatings, adhesive residue: ARDEX P 82™ Ultra Prime
 - Over metal: ARDEX EP 2000™ Substrate Preparation Epoxy Primer
- **Packaging:** 55 lb. (25 kg)
- Coverage: 30 sq. ft. per bag at 1/4" (2.8 m² at 6 mm)
- Thickness:
 - Levels at 1/4" (6 mm)
 - \bullet Installs from 1/8" to 1 1/2" (3 mm to 4 cm) neat
 - Up to 5" (13 cm) with aggregate
 - · Can be tapered
- Flow time: 10 minutes
- Walkable: 2 to 3 hours
- Install floor coverings:
- Moisture-insensitive tile and stone: 6 hours
 - All other floor coverings: 16 hours

Performance

- ASTM C191 Initial Set: Approx. 30 minutes
- ASTM C191 Final Set: Approx. 90 minutes
- ASTM C109 mod (air cure only) Compressive Strength: 5500 psi (386 kg/cm²) at 28 days
- ASTM C348 Flexural Strength: 1200 psi (84 kg/cm²) at 28 days
- VOC: 0















AF128 12/15

AMERICAS

CHOOSE

888-512-7339 +1-724-203-5000 www.ardexamericas.com

888-512-7339 prior to installation. For free ARDEX product training, click on ARDEX Academy.
© 2015 ARDEX Engineered Cements, L.P. All rights reserved.