



ARDEX ARDIFIX - Packaging and Recommendation Clarifications

We are writing to announce new information regarding ARDEX ARDIFIX.

Packaging

ARDEX ARDIFIX will now be available as a 2 gallon unit that contains 1 gallon each of parts A and B. This size will be offered in addition to the 22 oz. dual-cartridge dispenser.

Mixing and Application

The 2 gallon unit has its own mixing and application instructions.

Applications Without Aggregate

Shake parts A and B for 10 seconds each. Mix 1:1 by hand with a spatula or with a low-speed drill (300 - 400 rpm) and a mixing paddle attachment. Keep the paddle below the surface, and mix for 20 - 30 seconds. The material should be streak-free, but do not over mix. Immediately apply the material by pouring directly onto the repair area.

Applications With Aggregate

Shake parts A and B for 10 seconds each. Measure 2 parts sand to 1 part liquid. Quickly but thoroughly mix parts A and B by volume using a mixing paddle and a low-speed drill for 20 seconds maximum. Swiftly add the pre-measured sand, which must be saturated or wetted out. Rapidly scrape the bottom and sides of the bucket to ensure a good mix, and then swiftly pour and trowel the material onto the repair area. Pot life is 5 minutes or less. Warmer than average surface temperatures will decrease pot life.

Should you have any questions on this information, please contact the ARDEX Technical Service Department.

Tivona Schneider

Technical Communications Supervisor